

## SCHWEGO<sup>®</sup> eco foam 6321

Deaerator for non aqueous nature paints, VOC-free

**Chemical base:** Mixture renewable raw materials with polymers

**Properties:** **SCHWEGO<sup>®</sup> eco foam 6321** is a mixture of renewable raw materials with polymers. The content of renewable raw materials is in **SCHWEGO<sup>®</sup> eco foam 6321** 98% (ASTM D 6866). **SCHWEGO<sup>®</sup> eco foam 6321** prevents foam at the dispersion process and deaerates the film during the drying. **SCHWEGO<sup>®</sup> eco foam 6321** is a development special for non aqueous nature paints. But the use in conventional solvent-based paints is also possible. **SCHWEGO<sup>®</sup> eco foam 6321** is free of VOC.

**Applications:** **SCHWEGO<sup>®</sup> eco foam 6321** shows a good effect in following systems:

- Alkyd formulations with high content of renewable raw materials
- PUR-formulations based on polyols
- Epoxy formulations
- UV paints
- Conventional solvent-based paints

**Technical data:**  
(Guide values)

Appearance	:	clear, colorless liquid
Density (ISO 2811-1)	:	0.85 g/cm <sup>3</sup>
Flash point (ISO 1523)	:	> 110 °C
Active matter	:	100 %

**Processing:** **SCHWEGO<sup>®</sup> eco foam 6321** can be incorporated in the mill base, but in the let down is also possible, if **SCHWEGO<sup>®</sup> eco foam 6321** is homogeneously distributed. The dosage is dependent from the requirement. Normally between 0.1% - 1.0% , calculated at the ready paint. If necessary a higher dosage is also possible.

**Storage:** Stir **SCHWEGO<sup>®</sup> eco foam 6321** up before use. Keep it in a cool, well-ventilated place. Subject to appropriate storage, the described properties of **SCHWEGO<sup>®</sup> eco foam 6321** remain stable for at least 18 months, provided the original container is closed after use.

**Packaging:** 50 kg / 175 kg drum

The above information is based on our current knowledge and experience. No binding assurance in respect of certain properties or suitability for certain applications must be read into our information. Patent rights and other proprietary rights must be observed if necessary. Further safety instructions please learn from our material safety data sheet. 12/2022