

## ANTIGEL KF

Multifunctional additive for solvent borne and water-based coating systems | free of ketoxime | biodegradable

<b>Chemical base</b>	Antioxidant with additives in solvent mixture	
<b>Properties</b>	<p><b>ANTIGEL KF</b> has the following properties:</p> <ul style="list-style-type: none"> <li>• Stabilisation of viscosity against air oxidation</li> <li>• Prevention of skinning</li> <li>• Improved wetting</li> <li>• Prevention of settlement</li> <li>• Reduction of dispersing time</li> <li>• Removal of floatation phenomena</li> <li>• Promotion of flow and gloss</li> </ul>	
<b>Mode of action</b>	<p>The multifunctionality of <b>ANTIGEL KF</b> is based on the synergistic activity of the components.</p> <p><b>1. Viscosity stabilisation</b> The stabilisation is based on the oxygen binding properties of the antioxidant. <b>ANTIGEL KF</b> improves flow and through-drying.</p> <p><b>2. Wetting and dispersion</b> The wetting component of <b>ANTIGEL KF</b> reduces the interfacial tension between the usually hydrophilic pigments and the hydrophobic binder. The pigments are well distributed resulting an optimum depth of colour. Dispersion time, floatation phenomena and sedimentation are reduced and gloss is increased. Sedimentation is largely avoided. Because of the excellent wetting, optimum depth of colour is achieved.</p>	
<b>Applications</b>	<b>ANTIGEL KF</b> can be used in almost all water-based and solvent borne coating systems.	
<b>Technical data</b> (Guide values)	<p>Appearance</p> <p>Density (ISO 2811-1)</p> <p>Flash point (ISO 1523)</p>	<p>yellow - brown, clear liquid</p> <p>0.92 g/cm<sup>3</sup></p> <p>58 °C</p>
<b>Processing</b>	<p><b>ANTIGEL KF</b> should be added to the mill base in order to get optimum use of its wetting properties. It is recommended to establish the dosage by preliminary experiment.</p> <p><b>ANTIGEL KF</b> suited as multifunctional additive but recommended for anti-skinning properties and therefore used between 0.1 % and 0.5 % on total formulation while all other benefits will improve your</p>	

The above information is based on our current knowledge and experience.  
No binding assurance in respect of certain properties or suitability for certain applications must be read into our information.  
Patent rights and other proprietary rights must be observed if necessary.  
Further safety instructions please learn from our material safety data sheet.



formulation compared to traditional anti skinning additives.

## Storage

Keep **ANTIGEL KF** in a cool, well-ventilated place. Occasionally, slight sediment is formed, which does not adversely affect the quality of **ANTIGEL KF**. There is no need to stir up the sediment.

Subject to appropriate storage, the described properties of **ANTIGEL KF** remain stable for at least 2 years, provided the original container is closed after use.

## Packaging

50 kg drum | 200 kg drum



The above information is based on our current knowledge and experience.  
No binding assurance in respect of certain properties or suitability for certain applications must be read into our information.  
Patent rights and other proprietary rights must be observed if necessary.  
Further safety instructions please learn from our material safety data sheet.