

SCHWEGO® antimec 8010

Anti-skinning additive for water-based and solvent borne coating systems | free of ketoxime and aromates

Chemical base	Antioxidant in solvent mixture	
Properties	<p>SCHWEGO® antimec 8010 has the following properties / fields of application:</p> <ul style="list-style-type: none"> • Stabilisation of viscosity against air oxidation • Prevention of skinning 	
Mode of action	<p>1. Viscosity stabilisation The stabilisation is based on the oxygen binding properties of the antioxidant. SCHWEGO® antimec 8010 promotes flow and through drying.</p> <p>2. Prevention of skinning Thanks to a special ingredient reactions caused by oxygen are suppressed.</p>	
Applications	SCHWEGO® antimec 8010 is recommended in almost all water-based and solvent borne coating systems.	
Technical data (Guide values)	Appearance	yellow, clear liquid
	Density (ISO 2811-1)	0.91 g/cm ³
	Flash point (ISO 1523)	29.5 °C
Processing	SCHWEGO® antimec 8010 can be added to the coating at any formulation step. We recommend the addition at the let down process after the siccatives. The optimum dosage should be evaluated by preliminary laboratory experiments. An addition of 0.5 – 1.5 % calculated on total system is recommended.	
Storage	<p>Keep SCHWEGO® antimec 8010 in a cool, well-ventilated place. Occasionally, slight sediment is formed. This does not adversely affect the quality of SCHWEGO® antimec 8010 and there is no need to stir up the sediment.</p> <p>Subject to appropriate storage, the described properties of SCHWEGO® antimec 8010 remain stable for at least 2 years, provided the original container is closed after use.</p>	
Packaging	50 kg drum 200 kg drum	

The above information is based on our current knowledge and experience.
No binding assurance in respect of certain properties or suitability for certain applications must be read into our information.
Patent rights and other proprietary rights must be observed if necessary.
Further safety instructions please learn from our material safety data sheet.

