

SCHWEGO® antimec 8019

Anti-skinning additive for water-based and solvent borne coating systems | free of butanone oxime and aromates

Chemical base	Antioxidant in solvent mixture	
Properties	<p>SCHWEGO® antimec 8019 has the following properties / fields of application:</p> <ul style="list-style-type: none"> • Stabilisation of viscosity against air oxidation • Prevention of skinning 	
Mode of action	<p>1. Viscosity stabilisation The stabilisation is based on the oxygen binding properties of the antioxidant. SCHWEGO® antimec 8019 promotes flow and through drying.</p> <p>2. Prevention of skinning Thanks to a special ingredient reactions caused by oxygen are suppressed.</p>	
Applications	SCHWEGO® antimec 8019 is recommended in almost all water-based and solvent borne coating systems.	
Technical data (Guide values)	Appearance	light yellow to light brownish liquid
	Density (ISO 2811-1)	0.83 g/cm ³
	Flash point (ISO 1523)	16.5 °C
Processing	SCHWEGO® antimec 8019 can be added to the coating at any formulation step. We recommend the addition at the let down process after the siccatives. The optimum dosage should be evaluated by preliminary laboratory experiments. An addition of 0.2 – 1.0 % calculated on total system is recommended.	
Storage	<p>Occasionally, slight sediment is formed. This does not adversely affect the quality of SCHWEGO® antimec 8019 and there is no need to stir up the sediment.</p> <p>Subject to appropriate storage, the described properties of SCHWEGO® antimec 8019 remain stable for at least 2 years, provided the original container is closed after use.</p>	
Packaging	40 kg drum 160 kg drum	

