

## SCHWEGO® antimec 8021

Anti-skinning additive for water-based and solvent borne coating systems | free of butanone oxime and aromates

<b>Chemical base</b>	Antioxidant in solvent mixture	
<b>Properties</b>	<p>SCHWEGO® antimec 8021 has the following properties / fields of application:</p> <ul style="list-style-type: none"> <li>• Stabilisation of viscosity against air oxidation</li> <li>• Prevention of skinning</li> </ul>	
<b>Mode of action</b>	<p><b>1. Viscosity stabilisation</b> The stabilisation is based on the oxygen binding properties of the antioxidant. SCHWEGO® antimec 8021 promotes flow and through drying.</p> <p><b>2. Prevention of skinning</b> Thanks to a special ingredient reactions caused by oxygen are suppressed.</p>	
<b>Applications</b>	SCHWEGO® antimec 8021 is recommended in almost all water-based and solvent borne coating systems.	
<b>Technical data</b> (Guide values)	<p>Appearance</p> <p>Density (ISO 2811-1)</p> <p>Flash point (ISO 1523)</p>	<p>light yellowish to light brownish liquid</p> <p>0.82 g/cm<sup>3</sup></p> <p>16.0 °C</p>
<b>Processing</b>	SCHWEGO® antimec 8021 can be added to the coating at any formulation step. We recommend the addition at the let down process after the siccatives. The optimum dosage should be evaluated by preliminary laboratory experiments. An addition of 0.2 – 1.0 % calculated on total system is recommended.	
<b>Storage</b>	<p>Occasionally, slight sediment is formed. This does not adversely affect the quality of SCHWEGO® antimec 8021 and there is no need to stir up the sediment.</p> <p>Subject to appropriate storage, the described properties of SCHWEGO® antimec 8021 remain stable for at least 2 years, provided the original container is closed after use.</p>	
<b>Packaging</b>	40 kg drum   160 kg drum	

